



Spec Sheet – 1.5” Rebar Chair

TYPICAL RESIN PROPERTIES			
	ASTM TEST METHOD	VALUE	UNIT
MELT FLOW RATE:	D1238	18	G/10 min
DENSITY	D1505	0.900	G/CM3
TENSILE	D638	3,200	PSI
FLEXURAL MODULUS	D790	145,000	PSI
DEFLECTION TEMP	D648	180	F
HARDNESS VALUE	R-Scale	65	

<u>STRENGTH</u>

	VALUE	UNIT
MAXIMUM LOAD	1,599	LBS

<u>PRODUCT SPECIFICATIONS</u>

	VALUE	UNIT
<u>REINFORCEMENT GROUND CLEARANCE</u>	1.5	IN
<u>OVERALL HEIGHT</u>	2-5/8	IN
<u>CHAIR BASE DIMENSIONS</u>	3-5/8 X 3-5/8	IN
<u>CHAIR WEIGHT</u>	.05	LBS
<u>REINFORCEMENT BAR SIZE</u>	#4	